PATENT ABSTRACTS OF JAPAN

(11)Publication number :　　　　　2003-328078

(43)Date of publication of application : 19.11.2003

(51)Int.Cl.		C22C	38/00
		B25D	17/02
		C22C	38/54
		C23C	8/22
	//	C21D	1/06
		C21D	6/00
		C21D	9/00
		C21D	9/22
		C21D	9/32
		C21D	9/42

(21)Application number : 2002-135274

(22)Date of filing :　　　　10.05.2002

(71)Applicant : KOMATSU LTD

(72)Inventor : TAKAYAMA TAKEMORI

(54) HIGH-HARDNESS HIGH-TOUGHNESS STEEL AND TRACK-LAYING PARTS USING THE STEEL MATERIAL, SAND ABRASION RESISTANT PARTS, FASTENING BOLT, HIGH-TOUGHNESS TOOTHED GEAR, HIGH- TOUGHNESS HIGH-BEARING PRESSURE RESISTANCE TOOTHED GEAR, AND ABRASION RESISTANT STEEL SHEET

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a high-hardness high-toughness steel which more appropriately contains Si, Al, Cr, Mo, V, W, Ni and Co, and has hardness of HRC 50 or higher and a Charpy impact value of 5 kg-m/cm2 or higher, after being tempered at a high temperature of 600°C or higher.

SOLUTION: The high-hardness high-toughness steel is a tempered martensitic steel which comprises at least 0.15-1.2 wt.% C and 0.05-1.8 wt.% Si, 0.15-1.6 wt.% Al for substituting a part of Si, 0.3-2.5 wt.% added Ni, further 0.1-3.5 wt.% Cr and 0.1-1.7 wt.% Mo added so as to satisfy the expression of Mo (wt.%)=1.7-0.5×(Si (wt.%)+Al (wt.%)) as the upper limit, one or both of 0.05-0.40 wt.% added V and 0.1-1.0 wt.% added W, furthermore one or more alloying elements of Mn, Co, Cu, Ti, B and Nb, inevitable impurities like P, S, N and O, and the balance substantially Fe.

LEGAL STATUS

[Date of request for examination]　　　　18.01.2005

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of
rejection]
[Date of requesting appeal against examiner's
decision of rejection]
[Date of extinction of right]